JUKEN NEW ZEALAND LTD

PRODUCT QUALITY SPECIFICATIONS

PRODUCT	**Medium Density Fibreboard [MDF]**
PRODUCT CODE	**094 Line 1**
NOMINAL THICKNESS	**18 mm**
Common Usage	**General Purpose**

Property	Specification
Finished thickness [mm]	17.8 – 18.2
Finished board density [kg/m^3]	700 - 780

Physical Test	Specification
Internal bond - average [kPa]	Not Less than 400
MOR - average [Mpa]	Not Less than 15
MOE - average [Mpa]	Not Less than 1800

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Note

- Formaldehyde emissions meet the E1 class when tested in accordance with AS/NZS 4266.16:2004.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 9116
Facsimile: +64 9 408 9113
e-mail: sales@jnl.co.nz
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 7 June, 2002

JNL
JUKEN NEW ZEALAND LTD

PRODUCT SPECIFICATIONS

PRODUCT TYPE **Medium density fibreboard (MDF)**

PRODUCT CODE **097**

NOMINAL THICKNESS **21mm**

COMMON USAGE **Composite mould manufacture**

Property	Specification
Finished thickness [mm]	20.8 – 21.2
Finished board density [kg/m^3]	700 – 780
Surface density [kg/m^3]	700 – 780
Core density [kg/m^3]	700 – 780
Fibre resin type	MUF

Physical Test	Specification
Internal bond - average [kPa]	Not Less than 500
MOR - average [MPa]	Not Less than 18
MOE - average [MPa]	Not Less than 1800
Screw holding - average [N]	Not Less than 800
24 hour thickness swell [%]	Not Greater than 10

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 22 August 2005

JUKEN NEW ZEALAND LTD

PRODUCT QUALITY SPECIFICATIONS

PRODUCT Medium Density Fibreboard [MDF]

PRODUCT CODE 100

NOMINAL THICKNESS **25mm**

Property	Specification
Finished thickness [mm]	24.8 – 25.2
Finished board density [kg/m^3]	700 – 780

Physical Test	Specification
Internal bond - average [kPa]	Not Less than 400
MOR - average [Mpa]	Not Less than 14
MOE - average [Mpa]	Not Less than 1800
24 hour thickness swell [%]	Not Greater than 15

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Note

- Formaldehyde emissions meet the E1 class when tested in accordance with AS/NZS 4266.16:2004.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 9116
Facsimile: +64 9 408 9113
e-mail: sales@jnl.co.nz
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 7 June, 2002