PRODUCT SPECIFICATIONS

PRODUCT TYPE **Medium density fibreboard (MDF)**

PRODUCT CODE **093**

NOMINAL THICKNESS **9mm**

COMMON USAGE **General purpose**

Property	**Specification**
Finished thickness [mm]	8.8 – 9.2
Finished board density – nominal* [kg/m^3]	740

* Individual pieces of product may vary by up to 5% from nominal density

Physical Test	**Specification**
Internal bond - average [kPa]	Not Less than 500
MOR - average [MPa]	Not Less than 28
MOE - average [MPa]	Not Less than 2400
24 hour thickness swell [%]	Not Greater than 17

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Note

- Formaldehyde emissions meet the E 0 specifications as per amendment 1 of AS/NZS 1859.2:2004.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 24 June 2010

PRODUCT SPECIFICATIONS

PRODUCT TYPE **Medium density fibreboard (MDF)**

PRODUCT CODE **091**

NOMINAL THICKNESS **12mm**

COMMON USAGE **General purpose**

Property	**Specification**
Finished thickness [mm]	11.8 – 12.2
Finished board density – nominal* [kg/m^3]	740

* Individual pieces of product may vary by up to 5% from nominal density

Physical Test	**Specification**
Internal bond - average [kPa]	Not Less than 500
MOR - average [MPa]	Not Less than 28
MOE - average [MPa]	Not Less than 2400
24 hour thickness swell [%]	Not Greater than 17

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Note

- Formaldehyde emissions meet the E 0 specifications as per amendment 1 of AS/NZS 1859.2:2004.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 24 June 2010

PRODUCT SPECIFICATIONS

PRODUCT TYPE **Medium density fibreboard (MDF)**

PRODUCT CODE **099**

NOMINAL THICKNESS **16mm**

COMMON USAGE **General purpose**

Property	**Specification**
Finished thickness [mm]	15.8 – 16.2
Finished board density – nominal* [kg/m^3]	740

* Individual pieces of product may vary by up to 5% from nominal density

Physical Test	**Specification**
Internal bond - average [kPa]	Not Less than 450
MOR - average [MPa]	Not Less than 26
MOE - average [MPa]	Not Less than 2000
24 hour thickness swell [%]	Not Greater than 15

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Note

- Formaldehyde emissions meet the E 0 specifications as per amendment 1 of AS/NZS 1859.2:2004.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 24 June 2010

PRODUCT SPECIFICATIONS

PRODUCT TYPE **Medium density fibreboard (MDF)**

PRODUCT CODE **095**

NOMINAL THICKNESS **18mm**

COMMON USAGE **General purpose**

Property	**Specification**
Finished thickness [mm]	17.8 – 18.2
Finished board density – nominal* [kg/m^3]	740

* Individual pieces of product may vary by up to 5% from nominal density

Physical Test	**Specification**
Internal bond - average [kPa]	Not Less than 450
MOR - average [MPa]	Not Less than 26
MOE - average [MPa]	Not Less than 2000
24 hour thickness swell [%]	Not Greater than 15

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Note

- Formaldehyde emissions meet the E 0 specifications as per amendment 1 of AS/NZS 1859.2:2004.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 24 June 2010