JNL
JUKEN NEW ZEALAND LTD

PRODUCT QUALITY SPECIFICATIONS

PRODUCT	**Spaceboard**
PRODUCT CODE	**071**
NOMINAL THICKNESS	**36mm**
COMMON USAGE	**Solid core door**

Property	Specification
Finished thickness [mm]	35.8 – 36.2
Fibre thickness per side – nominal [mm]	2
Finished board density - nominal [kg/m^3]	540
Fibre density - nominal [kg/m^3]	810
Strand/core density - nominal [kg/m^3]	510

Note! Densities can vary from nominal by up to plus or minus 5%

Physical Test	Specification
Internal bond - average [kPa]	Not Less than 175
MOR - average [MPa]	Not Less than 10
MOE - average [MPa]	Not Less than 1800
Screw holding - average [N]	Not Less than 700
24 hour thickness swell [%]	Not Greater than 15

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Notes

- This product is identified by a green dyed core layer.
- Formaldehyde emissions meet the E zero class when tested in accordance with AS/NZS 4266.16.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 22 May 2009

JNL
JUKEN NEW ZEALAND LTD

PRODUCT QUALITY SPECIFICATIONS

PRODUCT **Spaceboard**

PRODUCT CODE **073**

NOMINAL THICKNESS **40mm**

COMMON USAGE **Door**

Property	Specification
Finished thickness [mm]	39.8 – 40.2
Fibre thickness per side - nominal [mm]	2
Finished board density [kg/m^3]	515 – 565
Fibre density [kg/m^3]	770 – 850
Strand/core density [kg/m^3]	485 – 535

Physical Test	Specification
Internal bond - average [kPa]	Not Less than 175
MOR - average [Mpa]	Not Less than 10
MOE - average [Mpa]	Not Less than 1800
Screw holding - average [N]	Not Less than 700
24 hour thickness swell [%]	Not Greater than 15

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 6 November, 2002