JUKEN NEW ZEALAND LTD

PRODUCT QUALITY SPECIFICATIONS

PRODUCT	**Strandboard**
PRODUCT CODE	**082**
NOMINAL THICKNESS	**9mm**
COMMON USAGE	**Floor overlay**

Property	Specification
Finished thickness [mm]	8.8 – 9.2
Finished board density - nominal [kg/m^3]	660

Note! Density can vary from nominal by up to plus or minus 5%

Physical Test	Specification
Internal bond - average [kPa]	Not Less than 500
MOR - average [Mpa]	Not Less than 18
MOE - average [Mpa]	Not Less than 2900
24 hour thickness swell [%]	Not Greater than 20

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Note

- Formaldehyde emissions meet the E1 classification when tested in accordance with AS/NZS 4266.16
- Wood is a natural material and colour variations between individual pieces of wood are normal. As such, some colour variations within and between individual Strandboard panels are a natural feature and are to be expected.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 3 August 2009

JUKEN NEW ZEALAND LTD

PRODUCT QUALITY SPECIFICATIONS

PRODUCT **Strandboard**

PRODUCT CODE **084**

NOMINAL THICKNESS **12mm**

Property	Specification
Finished thickness [mm]	11.8 – 12.2
Finished board density - nominal [kg/m^3]	660

Note! Density can vary from nominal by up to plus or minus 5%

Physical Test	Specification
Internal bond - average [kPa]	Not Less than 500
Bending strength (MOR) - average [MPa]	Not Less than 18
Modulus of Elasticity (MOE) - average [MPa]	Not Less than 2900
24 hour thickness swell [%]	Not Greater than 20

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Note

- Formaldehyde emissions meet the E1 class when tested in accordance with AS/NZS 4266.16.
- Wood is a natural material and colour variations between individual pieces of wood are normal. As such, some colour variations within and between individual Strandboard panels are a natural feature and are to be expected.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 3 August 2009

JNL
JUKEN NEW ZEALAND LTD

PRODUCT QUALITY SPECIFICATIONS

PRODUCT	**Strandboard**
PRODUCT CODE	**087**
NOMINAL THICKNESS	**20mm**
COMMON USAGE	**Flooring**

Property	Specification
Finished thickness [mm]	19.8 – 20.2
Finished board density - nominal [kg/m^3]	685

Note! Density can vary from nominal by up to plus or minus 5%

Physical Test	Specification
Internal bond - average [kPa]	Not Less than 500
Bending strength (MOR) - average [MPa]	Not Less than 17
Modulus of Elasticity (MOE) - average [MPa]	Not Less than 3000
Screw holding - average [N]	Not Less than 1200
24 hour thickness swell [%]	Not Greater than 14

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Note

- Formaldehyde emissions meet the E zero classification when tested in accordance with AS/NZS 4266.16.
- Wood is a natural material and colour variations between individual pieces of wood are normal. As such, some colour variations within and between individual Strandboard panels are a natural feature and are to be expected.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 14 October 2009

JUKEN NEW ZEALAND LTD

PRODUCT QUALITY SPECIFICATIONS

PRODUCT	**Strandboard**
PRODUCT CODE	**087TTT**
NOMINAL THICKNESS	**20mm**
COMMON USAGE	**Flooring (termite treated)**

Property	Specification
Finished thickness [mm]	19.8 – 20.2
Finished board density - nominal [kg/m^3]	685

Note! Density can vary from nominal by up to plus or minus 5%

Physical Test	Specification
Internal bond - average [kPa]	Not Less than 500
MOR - average [MPa]	Not Less than 17
MOE - average [MPa]	Not Less than 3000
Screw holding - average [N]	Not Less than 1200
24 hour thickness swell	Not Greater than 14

- These specifications apply to Triboard products ex. Mill.
- The test methods used are JNL in-house test methods except where specifically noted.
- These specifications supersede all previous specifications and are subject to change without notice.

Note

- Formaldehyde emissions meet the E zero classification when tested in accordance with AS/NZS 4266.16.
- Permethrin active content meets the requirements of AS 1604 for hazard class H2.
- Wood is a natural material and colour variations between individual pieces of wood are normal. As such, some colour variations within and between individual Strandboard panels are a natural feature and can be expected.

<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<<

JUKEN NEW ZEALAND LTD
TRIBOARD MILL
Whangatane Drive
Kaitaia, New Zealand

Telephone: +64 9 408 0300
Facsimile: +64 9 408 9113
www.triboard.com

An ISO 14001 and 9001 Certified Company.

Date of issue 14 October 2009